

## RF15/IRL 3321 Standard e Bicchierato - Serie "Ridge"



mt



min



max

### IMBALLO E CODICE ITALIA

Standard Bicchierato

	RF15016GS084	RF15016GB084	16	12,1	84	9240	27720
	RF15020GS084	RF15020GB084	20	15,9	84	6043	18129
	RF15025GS054	RF15025GB054	25	20,4	54	3888	11664
	RF15032GS042	RF15032GB042	32	26,8	42	2352	7056
	RF15040GS024	RF15040GB024	40	34,4	24	1512	4536
	RF15050GS015	RF15050GB015	50	43,3	15	960	2880

### VERPACKUNG UND CODE DEUTSCHLAND

Standard Gemüfft

	RF15016GS111	RF15016GB111	16	12,1	111	7770	23310
	RF15020GS111	RF15020GB111	20	15,9	111	4440	13320
	RF15025GS057	RF15025GB057	25	20,4	57	3420	10260
	RF15032GS057	RF15032GB057	32	26,8	57	1995	5985
	RF15040GS021	RF15040GB021	40	34,4	21	840	2520
	RF15050GS021	RF15050GB021	50	43,3	21	840	2520

					
	<b>TUBI PROTETTIVI ISOLANTI</b> RIGIDI, CURVABILI A FREDDO	<b>PROTECTIVE INSULATING</b> RIGID CONDUITS, COLD BENDING	<b>TUBE RIGIDE ISOLANT</b> CINTRABLE A FROID	<b>TUBOS AISLANTES RIGIDOS, PLEGABLE A FRÍO</b>	<b>STARRES ISOLIERWELLROHR</b> KALT BIEGSAM
	<i>Curvabili a freddo nei diametri 16-20-25 mm</i>	<i>Cold bending for diameters 16-20-25 mm</i>	<i>Cintrable a froid diam 16-20-25 mm</i>	<i>Plegable a frio en las diámetros 16-20-25 mm</i>	<i>Kalt biegsam für Durchmesser 16-20-25 mm</i>
	<b>MATERIALE</b> PVC	<b>MATERIAL</b> PVC	<b>MATERIEL</b> PVC	<b>MATERIAL</b> PVC	<b>MATERIAL</b> PVC
	<b>MARCHI DI QUALITÀ</b> IMQ NF-USE	<b>QUALITY MARKS</b> IMQ NF-USE	<b>CERTIFICATIONS DE QUALITÉ</b> IMQ NF-USE	<b>CERTIFICACIÓN DE CALIDAD</b> IMQ NF-USE	<b>QUALITÄTSZEICHEN</b> IMQ NF-USE
	<b>NORME</b> EN 61386.1 EN 61386.21	<b>STANDARDS</b> EN 61386.1 EN 61386.21	<b>STANDARDS</b> EN 61386.1 EN 61386.21	<b>NORMAS</b> EN 61386.1 EN 61386.21	<b>STANDARDS</b> EN 61386.1 EN 61386.21
	<b>RESISTENZA ALLA COMPRESIONE</b> Classe 3 medio (superiore a 750 N su 5 cm a +23°C)	<b>COMPRESSION RESISTANCE</b> Class 3 medium (higher than 750 N on 5 cm at +23°C)	<b>RÉSISTANCE À L'ÉCRASEMENT</b> Classe 3 médium (plus de 750 N sur 5 cm à +23°C)	<b>RESISTENCIA A LA COMPRESIÓN</b> Código 3 medio (750 N desde 5 cm a +23°C)	<b>DRÜCKFESTIGKEIT</b> Klasse 3 mittel (höher als 750 N auf 5 cm bei +23°C)
	<b>RESISTENZA ALL'URTO</b> Classe 3 medio (2 joule a -5°C)	<b>IMPACT RESISTANCE</b> Class 3 medium (2 joule a -5°C)	<b>RESISTANCE AUX CHOCS</b> Classe 3, médium (2 joule a -5°C)	<b>RESISTENCIA AL IMPACTO</b> Código 3 medio (2 joule a -5°C)	<b>SCHLAGSFESTIGKEIT</b> Klasse 3 mittel (2 joule bei -5°C)
	<b>TEMPERATURA MINIMA D'ESERCIZIO</b> Classe 2 (-5°C)	<b>MINIMUM TEMPERATURE RANGE</b> Class 2 (-5°C)	<b>TEMPÉRATURE MINIMALE D'EXERCICE</b> Classe 2 (-5°C)	<b>TEMPERATURA MÍNIMA DE UTILIZACIÓN</b> Código 2 (-5°C)	<b>MINDESTE-BETRIEBSTEMPERATUR</b> Klasse 2 (-5°C)
	<b>TEMPERATURA MASSIMA D'ESERCIZIO</b> Classe 1 (+60°C)	<b>MAXIMUM TEMPERATURE RANGE</b> Class 1 (+60°C)	<b>TEMPÉRATURE MAXIMALE D'EXERCICE</b> Classe 1 (+60°C)	<b>TEMPERATURA MÁXIMA DE UTILIZACIÓN</b> Código 1 (+60°C)	<b>MAXIMALE-BETRIEBSTEMPERATUR</b> Klasse 1 (+60°C)
	<b>RESISTENZA ALLA PROPAGAZIONE DELLA FIAMMA</b> Autoestinguento	<b>FLAME PROPAGATION RESISTANCE</b> Self-extinguishing	<b>RESISTANCE À LA PROPAGATION DE LA FLAMME</b> Autoextinguible	<b>RESISTENCIA A LA PROPAGACION DE LA LLAMA</b> No propagador	<b>FLAMMWIDRIGKEIT</b> Selbstverlöschend
	<b>RESISTENZA ELETTRICA DI ISOLAMENTO</b> Superiore a 100 mohm a 500 V per 1 minuto	<b>ELECTRIC INSULATING RESISTANCE</b> Higher than 100 mohm for 500 V in 1 minute	<b>RESISTANCE ELECTRIQUE D'ISOLEMENT</b> Plus de 100 mohm (tension de 500 V pour 1 minute)	<b>RESISTENCIA ELÉCTRICA DE AISLAMIENTO</b> Superior a 100 mohm a 500 V por 1 minuto	<b>ELEKTRISCHER SCHUTZ</b> Höher als 100 mohm für 500 V in 1 minuten
	<b>RIGIDITÀ DIELETRICA</b> Superiore a 2000 V 50 Hz per 15 minuti	<b>DIELECTRIC STRENGTH</b> Higher than 200 V at 50 Hz for 15 minutes	<b>RIGIDITÉ DIÉLECTRIQUE</b> Plus de 2000 V à 50 Hz pendant 15 minutes	<b>RIGIDEZ DIELECTRICA</b> Superior a 2000 V 50 Hz por 15 minutos	<b>DIELEKTRISCHER WIDERSTAND</b> Höher als 2000 V bei 50 Hz für 15 minuten